


F-WAPWHITE OPAQUE BOPET FILM

F-WAP is a white opaque BOPET film. The film is one side corona treated or both side untreated.

KEY FEATURES:

- Excellent opacity & high brightness
- Excellent machinability & handling properties
- Good mechanical & thermal properties
- Corona treated side gives good adhesion with inks & adhesives

FILM STRUCTURE



APPLICATION:

- Surface printing jobs & metallization
- Label application & blister packaging
- Other conversion where white backing required like lids

PROPERTIES	TEST METHOD	UNIT	TYPICAL VALUES			
THICKNESS	Internal	Micron	12	23	36	50
ITICKNESS	internal	(Gauge)	48	92	144	200
YIELD	Internal	m² / kg	58.27	30.40	19.42	13.98
TIELD	internai	in² /lb	41022	21401	13671	9841
SURFACE TENSION (min) # (Corona Treated Side)	ASTM D-2578	dyne/cm	52			
COF (max)	ASTM D-1894	-	0.50	0.50	0.50	0.50
(Corons to Untreated side) (Untreated to Untreated side)	ASTM D-1894		0.45	0.45	0.45	0.45
OPACITY (min)	Hunter Lab	%	55	75	82	85
TENSILE STRENGTH AT BREAK (min) MD MD TD	MD	kg/cm²	1700	1600	1500	1500
	TD ASTM D-882		2000	2000	2000	2000
	MD ASTIVI D-882	(Psi)	24200	21300	21300	21300
	TD		28500	28500	28500	28500
ELONGATION AT BREAK (min)	MD ASTM D-882	%	110	115	120	125
	TD A31W D-002		80	80	85	85
LINEAR SHRINKAGE (max) MD (30 Minute at 150°C) TD	MD ASTM D-1204	%	2.5			
			0.8			
W.V.T.R. (38° C & 90% RH) (typical)	ASTM F-1249	gm/m²/day	45	25	15	12
vi.v.i.i. (30° C & 30% Ki i) (typical)		(gm/100 in²/day)	2.9	1.6	1.0	0.8
OTR (23°C & 0% RH) (typical)	ASTM D-3985	cc/m²/day	160	75	45	35
orrelation of the state of the	1.2.1	(cc/100 in²/day)	10.3	4.8	2.9	2.2

[#] The inherent surface tension of the untreated side of any Pet film is minimum 42 dyne/cm

STORAGE & HANDLING

FLEXPET[™] need to be stored in a warehouse below 35°C (95° F) and should not be exposed to direct sunlight, bright light sources or high humidity. If the material is stored in the recommended conditions, FLEXPET[™] is suitable for use within 270 days from date of shipment.

FOOD CONTACT

FLEXPETIN complies with EU and FDA regulations on plastic materials used for food grade application. Specific document and SDS are available on request.

DISCLAIMER

It is the responsibility of our customers to determine that their use of our products is safe, lawful, and technically suitable in their intended applications. The technical data sheets are provided for discussion purposes only. The customer may not rely on the data provided for any manufacturing purpose. The values provided in the technical data sheet represent typical values based on the best of our knowledge as of the date when the data was compiled. The data is offered solely to provide possible suggestions for your own experimentation and not as a guarantee for the material supplied. The user is solely responsible for the end use of the product and needs to perform their own tests to confirm the product suitability/compatibility in all respects. Flex provides no warranty and accepts no liability for any loss or fitness of the product for any specific purpose based on the information contained in the technical data sheets. Flex reserves the right to change the technical data sheet at any time without prior notice.

FlexFilms

Manufacturing Facilities at India | UAE | Poland | Egypt | Mexico | USA | Hungary | Russia | Nigeria ⊠ enquiry@flexfilm.com ∰ www.flexfilm.com